



TF-15[®]

METAL-FREE THREAD SEALING COMPOUND

DESCRIPTION

TF-15 Thread Sealing Compound is a high-pressure sealant containing PTFE, graphite and rust, corrosion, and oxidation inhibitors. All are blended in **JET-LUBE's** complex grease manufactured using highly refined, low-sulfur oil to ensure brushability over a wide temperature range, tenacious adherence to all surfaces, resistance to water washout, and prevention of rust/corrosion. **TF-15** is highly recommended for use on fiberglass casing and tubing on cut threads. Formed threads can have tighter clearances and require the use of TF-15 Arctic.

TF-15 assures tight makeup at low torque and allows easy breakout without seizing, stripping, or galling. It provides a permanent seal and maintains joint efficiency under vibration, pressure, surge, and temperature fluctuations. It is particularly useful in areas subject to H₂S*, salt water, a wide variety of oils, solvents, gases (except oxygen), acids, alkalis and steam.

- H₂S Inhibited.
- Non Metallic, Non Volatile, Solvent Free
- Lubricates for tighter makeup with less torque
- Seals at temperatures to 600°F
- Seals at pressures to 10,000 psi
- Seals badly worn threads as tight as new
- Seals applications exposed to H₂S and salt water
- Available in Arctic grade
- Conforms with API 5A3 for use with casing, tubing, and line pipe.

APPLICATIONS

TF-15 is expressly formulated for precision threads of API oilfield casing, tubing, line pipe, subsurface production tools, and related accessories. It prevents galling and thread wear, seals badly worn threads, and greatly increases connection life.

TF-15 can be used on PVC.

SERVICE RATING:

Application Temperature: -30°F (-34°C) to 200°F (93°C)
Sealing Temperature to 600°F (315°C)
Pressures to 10,000 psi

PRODUCT CHARACTERISTICS

Thickener	Complex
Fluid Type	Petroleum
Color	Black
Dropping Point (ASTMD-2265)	450°F (232°C)
Specific Gravity	1.21
Density (lb/gal)	10.1
Oil Separation	<3.0
WT. % LOSS @212°F (100°C)	
Flash Point (ASTM D-92)	>430°F (221°C)
NLGI Grade	1½
Penetration@77°F (ASTMD-217)	275 - 305
Copper Strip Corrosion (ASTM D-4048)	1A
4-Ball (ASTM D-2596)	
Weld Point, kgf	620
Friction Factor (Relative to API-MODIFIED)	0.7
EPA 1311-TCLP	Non-detected

For package types and part numbers

www.jetlube.com/resources/product-index/

Limited Warranty

www.jetlube.com/assets/documents/Jet-Lube_Warranty.pdf